

BULLETIN

Double Poly Film

Opacity of Double Poly

The table below is intended as an aid in the selection process when using two partially opaque films on the same structure.

Example (refer to the table):

Film A—opacity = 55%

Film B—opacity = 70%

Opacity of two films combined = 77%


It does not matter whether film A or B is the outside film.

Note that the table contains some film opacities that we currently do not offer and are only listed for informational purposes. The results in the table were obtained from actual film test data.

		Opacity of Film A										
		35	40	45	50	55	60	65	70	75	80	85
Opacity of Film B	35	48	51	55	58	62	66	69	73	77	81	86
	40	51	53	57	60	63	67	71	73	77	82	86
	45	55	57	60	63	66	69	72	75	78	83	87
	50	58	60	63	65	68	71	73	76	80	84	87
	55	62	63	66	68	71	73	75	77	81	84	88
	60	66	67	69	71	73	75	76	78	82	85	88
	65	69	71	72	73	75	76	78	80	83	86	89
	70	73	73	75	76	77	78	80	81	85	87	89
	75	77	77	78	80	81	82	83	85	87	88	90
	80	81	82	83	84	84	85	86	87	88	90	91
	85	86	86	87	87	88	88	89	89	90	91	92

The above data are typical values provided for informational purposes only and should not be construed as a specification.



 100% recyclable 100% FDA compliant

AT Films, Inc.
P.O. Box 836 Station Main
Edmonton, AB Canada
T5J 2L4

Toll-Free: 1-800-661-3606
Phone: (780) 450-7760
Fax: (780) 450-7777
Email: info@atfilmsinc.com
www.atfilmsinc.com